

FLUOROPOLYMERIC ORTHODONTIC ARTICLE

5

Background of the Invention

This invention relates to fluoropolymeric orthodontic articles.

Orthodontic treatment often involves the application of mechanical forces to urge improperly positioned teeth into correct alignment. One common form of orthodontic treatment includes the use of orthodontic brackets affixed to the surface of a  
10 tooth; and a resilient curved arch wire seated in slots on the brackets. The arch wire exerts a restoring force on the teeth which tends to shift the teeth into orthodontically correct alignment.

Orthodontic articles such as, e.g., brackets, were traditionally formed from metal, but more recently have been formed from plastic and ceramic. Plastic brackets can  
15 be fabricated to be translucent to transparent in character relative to metal brackets. It is often difficult, however, to maintain the aesthetic characteristics of plastic brackets during use because food and beverages can stain and discolor the brackets while they reside in a patient's mouth.

Summary of the Invention

20 In one aspect, the invention features an orthodontic article (e.g., an orthodontic bracket) that includes a fluoropolymer and that exhibits at least about 0.001 % transmittance at 546 nm when measured according to the Transmittance Test Procedure described herein. In another embodiment, the article exhibits at least about 0.01 % transmittance at 546 nm when measured according to the Transmittance Test  
25 Procedure. In other embodiments, the article exhibits a transmittance of at least about 0.001% over a wavelength range of from 400 nm to 800 nm when measured according to the Transmittance Test Procedure.

03252628-030495

In one embodiment, the article exhibits a Delta E color shift of no greater than about 2 when tested according to the Hydrophilic Color Shift Test, and a Delta E color shift of no greater than about 5 when tested according to the Oleophilic Color Shift Test.

Suitable fluoropolymers are selected from the group consisting of

5 perfluoroethylene-propylene copolymer, perfluoroalkoxyethylene, ethylene-tetrafluoroethylene copolymer, polyvinylidene fluoride, polyvinyl fluoride, polychlorotrifluoroethylene, ethylene-chlorotrifluoroethylene copolymer, and combinations thereof. In one embodiment, the fluoropolymer includes perfluoroethylene-propylene copolymer. In another embodiment, the fluoropolymer

10 includes perfluoroalkoxyethylene. In other embodiments, the fluoropolymer includes ethylene-chlorotrifluoroethylene copolymer.

The article may further include a polymeric composition disposed on a surface of the article, where the polymeric composition includes an organoborane compound. In another embodiment, the article further includes an organoborane amine complex

15 disposed on a surface of the article.

In another aspect, the invention features a method for using an orthodontic bracket, where the method includes: (a) contacting a fluoropolymeric orthodontic bracket having an average transmittance of at least 0.001 % when measured according to the Transmittance Test Method with a composition that includes an organoborane

20 compound; and (b) adhering the bracket to a tooth. In one embodiment, the method further includes: contacting the surface that includes an organoborane compound with a polymerizable component; and polymerizing the polymerizable component to form an adhesive composition. In other embodiments, the method further includes contacting a polyimide film with the composition that includes the organoborane compound prior to

25 adhering the bracket to a tooth.

In another embodiment, the method further includes treating the organoborane treated surface with a polymerizable component, and polymerizing the polymerizable

component. In one embodiment, the method further includes contacting the polymerized component treated surface with an adhesive composition.

In another aspect the invention features an orthodontic article that includes a fluoropolymer selected from the group consisting of perfluoroethylene-propylene copolymer, perfluoroalkoxyethylene, ethylene-tetrafluoroethylene copolymer, polyvinylidene fluoride, polyvinyl fluoride, polychlorotrifluoroethylene, ethylene-chlorotrifluoroethylene copolymer, and combinations thereof. In one embodiment, the orthodontic article includes a bracket. The orthodontic article may further include a metallic component.

In another aspect, the invention features a kit for adhering an orthodontic article to a tooth. The kit includes an orthodontic article that includes a fluoropolymer having at least about 0.001% transmittance at 546 nm when measured according to the Transmittance Test Procedure; and an adhesive system that includes a) a polymerizable component; and b) an organoborane amine complex. In one embodiment, the organoborane amine complex is disposed on a surface of the orthodontic article. In another embodiment, the kit further includes a polyimide film.

The orthodontic articles are resistant to staining by food and beverages such as mustard and spaghetti sauce such that the article remains aesthetically pleasing in appearance and does not unduly darken or turn yellow during the time the article remains in the oral cavity. The orthodontic articles also maintain their essentially translucent to transparent character over the useful life of the article such that they transmit the color of the underlying tooth surface to which they are adhered.

Other features and advantages of the invention will be apparent from the following description of the preferred embodiments thereof, and from the claims.

#### Brief Description of the Drawing

FIG. 1 is a front view looking toward a buccolabial side (i.e., toward a lip or cheek facing side) of an orthodontic bracket;

FIG. 2 is an end view of the orthodontic bracket of FIG. 1;  
FIG. 3 is a front view looking toward a buccolabial side (i.e., toward a lip or  
cheek facing side) of a second embodiment of an orthodontic bracket;  
FIG. 4 is an end view of the orthodontic bracket of FIG. 3;  
5 FIG. 5 is a front view of a third embodiment of a test article;  
FIG. 6 is a perspective side view of the test article of FIG. 5;  
FIG. 7 is a plot of % transmittance versus wavelength (nm) for the bracket of  
Example 12;  
FIG. 8 is a plot of % transmittance versus wavelength (nm) for the bracket of  
10 Example 13;  
FIG. 9 is a plot of % transmittance versus wavelength (nm) for the bracket of  
Example 14;  
FIG. 10 is a plot of % transmittance versus wavelength (nm) for the bracket of  
Example 15;  
15 FIG. 11 is a plot of % transmittance versus wavelength (nm) for the bracket of  
Example 16;  
FIG. 12 is a plot of % transmittance versus wavelength (nm) for the bracket of  
Comparative Example 1;  
FIG. 13 is a front view looking toward a buccolabial side of an embodiment of  
20 an orthodontic bracket that includes a metallic framework;  
FIG. 14 is a front view looking toward a buccolabial side of another  
embodiment of an orthodontic bracket that includes a metallic framework; and  
FIG. 15 is a perspective view of the metallic framework of FIG. 14.  
FIG. 16 is a side view of another embodiment of an orthodontic bracket that  
25 includes a fluoropolymeric layer on a nonfluoropolymeric interior.

### Description of the Preferred Embodiments

Orthodontic articles are capable of being mounted on a tooth, and are used to transmit to the tooth a corrective force from an arch wire, spring, elastic, or other activatable force-applying component.

5           FIGS. 1 and 2 show an exemplary orthodontic article in the form of an orthodontic bracket 10. The bracket has a base 11 suitable for either direct bonding to a tooth or attachment to any kind of mounting fixture. A tooth facing surface 12 of the base 11 can be concavely curved about both mesiodistal axis and an apical axis to match the natural convexity of the tooth labial surface, but other curvatures or flat surfaces can  
10 also be used to accommodate bracket positioning. A bracket body 13 extends from base 11 to define bracket tie-wings 14 for ligature anchorage, and a mesiodistally oriented arch-wire slot 15 extending from an outer body surface 16 into the bracket body.

          FIGS. 3 and 4 depict a second embodiment of an orthodontic bracket 20 as seen from the buccolabial side and from the end, respectively. FIGS. 5 and 6 depict a test  
15 article 30 in which a slot 35 is seen from the top in FIG. 5. The article is shown in perspective side view in FIG. 6. The test article of FIGS. 5 and 6 approximates the overall size and thickness of a conventional orthodontic bracket.

          The fluoropolymeric orthodontic articles described herein are resistant to staining during use such that the articles maintain their original color as determined by  
20 the unaided human eye under common lighting conditions (e.g., sunlight and incandescent light). The fluoropolymeric orthodontic articles are resistant to staining from oil-based staining agents such as, e.g., spaghetti sauce, and water-based staining agents such as, e.g., mustard. Preferably the fluoropolymeric orthodontic articles exhibit a Delta E color shift of less than 2 (more preferably less than 1, and most preferably 0)  
25 when tested according to the hydrophilic color shift test procedure set forth below, and a Delta E color shift of less than 5 (more preferably less than 3, and most preferably 0) when tested according to the oleophilic color shift test procedure set forth below.

The orthodontic articles appear translucent to transparent to the human eye such that when the article is placed on a surface such as, e.g., a tooth, the article transmits the color of the underlying surface through the article. Preferably the article exhibits at least about 0.001% transmittance at 546 nm, more preferably 0.01% transmittance at 546 nm when measured according to the Transmittance Test Procedure set forth below. Preferred articles exhibit a transmittance of at least about 0.001% over the wavelength range of 400 nm to 800 nm when measured according to the Transmittance Test Procedure.

The fluoropolymeric orthodontic articles include fluoropolymer resins that are capable of being hardened and have sufficient strength, hydrolytic stability, and non-toxicity to render them suitable for use in the mouth. The fluoropolymers are translucent to transparent. Preferred fluoropolymers exhibit at least about 0.001% transmittance, more preferably 0.01% transmittance, at 546 nm when measured according to the Transmittance Test Procedure. Useful fluoropolymers include perfluoroethylene-propylene copolymer, perfluoroalkoxyalkane, ethylene-tetrafluoroethylene copolymer, polyvinylidene fluoride, polyvinyl fluoride, polyfluorotrifluoroethylene, ethylene-chlorotrifluoroethylene copolymer, and combinations thereof.

Examples of useful commercially available fluoropolymers include: Tefzel HT 2004 ethylene-tetrafluoroethylene copolymer including glass fibers, Tefzel 200, Tefzel 220, Tefzel 280, Tefzel 210, HT 2055, HT 2055NA, HT 2088NA, HT 2098, HT 2118, HT 2141, HT 2155 and HT 2158 ethylene-tetrafluoroethylene copolymers, Teflon PFA 340 perfluoroalkoxy fluorocarbon resin, and Teflon AF 1600 and Teflon AF 2400 perfluoro(2,2-dimethyl-1,3-dioxole)-tetrafluoroethylene copolymer (all available from DuPont); Hyflon PFA tetrafluoroethylene-perfluorovinylether copolymer, and Halar, Halar 300 and Halar 500 DA ethylene-chlorotrifluoroethylene copolymer (all available from Ausimont); Kel-F 81 PCTFE polychlorotrifluoroethylene (available from Minnesota

Mining and Manufacturing), and the line of fluoropolymers available under the trade designation "THV" from Dyneon, LLC (Oakdale, Minnesota).

Preferred adhesive systems for bonding a fluoropolymeric article to a tooth surface include a primer composition and a polymerizable component. The primer composition is capable of enabling or enhancing the adhesion of a fluoropolymeric article to the surface of a tooth. Useful primer compositions include an organoborane amine complex capable of initiating polymerization of a polymerizable component. The polymerizable component may include, e.g., monomers, oligomers, and combinations thereof that are capable of polymerizing and thereby forming an adhesive composition.

Preferred adhesive systems also include an effective amount of a compound that is reactive with or will remove the amine portion of the organoborane amine complex so as to liberate the organoborane and thereby allow the organoborane to initiate polymerization of polymerizable components.

Examples of useful organoborane amine complexes and adhesive systems that include an organoborane amine complex are described, e.g., in U.S. Patent Nos. 5,539,070 (Zharov et al.), 5,616,796 (Pocius et al.), 5,681,910 (Pocius), and 5,310,835 (Skoultchi et al.), and in WO 98/17694 and WO 97/07151, each of which is incorporated herein.

The fluoropolymeric orthodontic article, the tooth, or a combination thereof, can be treated (i.e., primed) with a primer composition prior to adhering the article to the tooth. One example of a useful priming composition is Transbond XT Light cure priming composition (Minnesota Mining and Manufacturing ("3M"), St. Paul, MN). Other useful priming compositions are described in U.S. Patent No. 5,558,516 (Horn et al.) and incorporated herein. The above-described organoborane amine adhesive compositions are also suitable priming compositions.

One example of a useful method for adhering the fluoropolymeric orthodontic article to the surface of a tooth includes contacting the orthodontic article with an

adhesive composition and adhering the orthodontic article to the tooth surface. The method can include priming a surface, e.g., the surface of the tooth, the orthodontic article, and combinations thereof, with a priming composition prior to adhering the orthodontic article to the surface of the tooth. The surface can be primed with one or  
5 more priming compositions sequentially, simultaneously and in combinations thereof. In one preferred method, the surface is primed with a composition that includes an organoborane amine complex. In another preferred method, the surface can be pretreated, e.g., primed, and then packaged for later use as described, for example, in U.S. Patent No. 5,558,516 (Horn et al.) and incorporated herein. After pretreatment, the  
10 surface can be treated with a primer composition, an adhesive composition and combinations thereof.

## EXAMPLES

### Transmittance Test Procedure

The % transmittance of light through an article is measured as follows. An  
15 article is placed in the well of a glass well slide such that the tooth contacting surface of the article is in contact with the slide. The well is filled with immersion liquid having a refractive index ("ND") of 1.515 and covered with a coverslip. The bracket containing slide is then placed under a microscope having a 3.2x objective, a numerical aperture ("N.A.") of 0.06, and a substage condensing lens system having a 0.3 N.A. The aperture  
20 and field diaphragms on the substage condensor are set up to produce the standard transparency by transmission measurement configuration (t(o/180)) of ASTM E-179-91a "Standard Guide for the Selection of Geometric Conditions for Measurement of Reflection and Transmission Properties of Materials."

The area of the article that is of interest is then brought into focus. The slide  
25 is then moved such that a reference area is brought into view (the focus of the microscope is not changed during this procedure). The reference area is an area within the well that contains immersion oil but does not contain the article. A calibration spectrum is



collected from the reference area and is defined as having a transmittance of 1.0 over the wavelength range. The slide is then moved such that the area of interest of the article is brought into the field of view and the transmittance spectrum is collected over a predetermined wavelength or wavelength range e.g., 400 nm to 800 nm.

- 5           A series of measurements are taken at a number of locations on the article that are visible to an observer when the article is worn by a user, see, e.g., the numbers and letters indicated on FIGS. 3, 4, 5, 6 and 13. The measurements are taken in a labial-lingual direction along paths that extend from the labial-most surface of the article to the lingual-most base of the article, being careful to avoid areas in which a metal object is
- 10 present in the article and would interfere with the path of the beam of radiation. The lowest transmittance value obtained for the article at a given wavelength is the transmittance of the article at that wavelength.

#### Color Measurement and Calculation Test Procedure

- 15           The color shift in an article is measured as follows. A LABSPHERE certified diffuse white reflectance standard (CSS-99-010 8812A) is placed on the stage of a Leitz Orthoplan Microscope equipped with a Leitz MPV-SP Spectrophotometer illuminated with a tungsten halogen lamp. The microscope is set to 3.2x objective with a numerical aperture ("N.A.") of 0.06. A fiber optic ring, which produces a 45 degree cone of
- 20 illumination, is mounted on the objective lens of the microscope producing a standard 45° illumination/ 0° detection color measurement (R(45/0)) according to ASTM E-179-91a, "Standard Guide for the Selection of Geometric Conditions for Measurement of Reflection and Transmission Properties of Materials."

- The spectrophotometer is set to a measuring spot of 1mm x 1mm, slit width of
- 25 6 nm, threshold of 1, high voltage of 480v, filter edge 100Hz, and integration 8x. Two scans are taken from 370 nm to 800 nm at a sampling rate of 1/3 nm and data is reported every 1 nm.

The lamp intensity of the halogen lamp is adjusted such that the signal is never greater than 90% of that needed to saturate the detector. A calibration spectrum is collected from the area and is defined as having a reflectivity of 100% over the wavelength range. The reflectance standard is removed and a sample is placed on the microscope stage. An area of interest is brought into crisp focus and a reflectance spectrum is collected. The reflectance standard is returned to the microscope stage, brought into focus and the reflectance spectrum is collected. If the spectrum collected is other than 100% for the second measurement of the standard over the wavelength range, the standardization steps are repeated.

The color measurements and calculations are performed in accordance with ASTM standards E-308-95, "Standard Practice for Computing the Colors of Objects by Using the CIE System," and D 2244-93, "Standard Test Method for Calculation of Color Differences from Instrumentally Measured Color Coordinates" using the L\*a\*b\* color representation. The L\* value is a measure of the brightness of the sample. The a\* is a measure of the redness for a positive value or greenness for a negative value, and b\* is a measure of yellowness for a positive value or blueness for a negative value. Color differences (i.e.,  $\Delta L^*$ ,  $\Delta a^*$  and  $\Delta b^*$ ) are calculated by subtracting the reference value from the sample value. The total color shift is represented by delta E according to the following formula:

$$\Delta E = \sqrt{\Delta L^{*2} + \Delta a^{*2} + \Delta b^{*2}}$$

#### Hydrophilic Color Shift Test Procedure

The color shift exhibited by an article after contact with a hydrophilic substance is measured as follows. Specimens are immersed for one hour at 60°C in French's 100% pure prepared yellow mustard. The samples are then removed, rinsed thoroughly with water, and air-dried.

The samples are then tested according to the above Color Shift Measurement and Calculation Test Procedure to determine Delta E.

#### Oleophilic Color Shift Test Procedure

5           The color shift exhibited by an article after contact with an oleophilic substance is measured as follows. Specimens are immersed for 2.5 hours at 60°C in Ragu Old World Style Flavored Spaghetti sauce with meat. The samples are then removed, rinsed thoroughly with water, and air-dried. The samples are then tested according to the above Color Shift Measurement and Calculation Test Procedure to  
10 determine Delta E.

#### Staining Test Procedure

##### **Example 1**

A 1 cm x 1 cm x 3 mm sample of Ausimont PFA 450 perfluoroalkoxy  
15 fluorocarbon resin (Ausimont) was immersed in French's mustard for period of two weeks at 60°C. The sample was then removed, washed with water, dried and adhered onto a white paper chart. Visual observations regarding the degree of staining were made and recorded. The results are summarized in Table I.

Additional samples of the Ausimont PFA 450 were immersed in either Ragu  
20 spaghetti sauce, chili powder (Spice Island) at 1g per 10g water, or curry powder (Shilling) at 1g per 10g water. The samples remained in the staining agents for two weeks at 60°C. After two weeks the samples were removed, washed with water, and adhered to a chart. Visual observations regarding the degree of staining were made and recorded. The results are summarized in Table I.

### **Example 2**

1 cm x 1 cm x 3 mm samples of Ausimont Halar polyethylene-chlorine trifluoroethylene were stain tested as in Example 1. No staining was observed.

### **5 Example 3**

1 cm x 1 cm x 3 mm samples of DuPont PFA 340 perfluoroalkoxy fluorocarbon resin (DuPont) were stain tested as in Example 1. No staining was observed.

### **10 Example 4**

1 cm x 1 cm x 3 mm samples of Tefzel 210 ethylene-tetrafluoroethylene (DuPont) were stain tested as in Example 1. No staining was observed for the samples immersed in spaghetti sauce, mustard, and chili. A very light yellow was observed for the sample immersed in curry.

15

### **Example 5**

1 cm x 1 cm x 3 mm samples of Tefzel 280 ethylene-tetrafluoroethylene (DuPont) were stain tested as in Example 1. No staining was observed.

20

The results obtained in Examples 1-5 are summarized in Table I.

**TABLE I**

<b>Sample</b>	<b>Spaghetti Sauce</b>	<b>Mustard</b>	<b>Chili</b>	<b>Curry</b>
Example 1	None	None	None	None
Example 2	None	None	None	None
Example 3	None	None	None	None
Example 4	None	None	None	v. Light yellow
Example 5	None	None	None	None

### Bond Strength Test Method

Samples are adhered to a knurled steel ring and immersed in a 37°C water bath for 16-24 hours. The ring with bonded samples is removed from the water, air-dried, and then placed onto the test fixture of an Instron Universal tensile test equipment.

- 5 A wire loop is placed into the upper jaw of the test fixture and through the sample such that it is affixed to the sample. The wire is then pulled by the upper jaw of the test fixture at a rate of 0.2 inches per minute (0.5 cm/min) at a full scale load of 100 lbs (45 kg). The bond strength (in pounds) at separation of the sample from the metal ring is recorded.

### 10 Primer Composition Preparation

A primer composition was prepared by combining:

- 3.5 parts by weight of a monomer mixture of 39 parts by weight methyl methacrylate, 28 parts by weight butyl acrylate, 3 parts by weight methacrylic acid, 30 parts by weight poly(methylmethacrylate-co-ethyl acrylate (mol. wt. 101,000 (Aldrich))),  
15 and 100 parts by weight of a complex of triethylborane and Dytek A 2-methyl-1,5-pentane diamine, having one equivalent of boron per equivalent of nitrogen, and mixing with a wooden stick.

### Sample Preparation

#### 20 **Example 6**

- The 0.231 cm x 0.330 cm surface of a 0.231 cm x 0.330 cm x 0.183 cm embossed cube of Halar 500DA ethylene-chlorotrifluoroethylene copolymer (available from Ausimont U.S.A. Inc.) was dipped into the above-described primer composition such that the primer composition completely covered the surface. The primed surface  
25 was then pressed against a grooved, knurled steel bonding ring, such that the cube adhered to the bonding ring, and the primer composition was allowed to cure for 48 hours.

The cube was then tested according to the Bond Strength Test Method. The results are reported in Table II.

#### **Example 7**

5           A dab of primer composition prepared as described above was coated onto a polyimide film. The 0.231 cm x 0.330 cm surface of a 0.231 cm x 0.330 cm x 0.183 cm embossed cube of Halar 500DA ethylene-chlorotrifluoroethylene copolymer (Ausimont) was dipped into the primer composition such that a face of the cube was completely covered with the primer composition. The primer composition was allowed to cure for  
10 48 hours, after which the cube was peeled from the polyimide film. Transbond XT light cure primer composition (3M) was then applied to the primed surface of the cube. The Transbond XT primer was allowed to sit for 60 seconds and then cured with visible light. The primed surface was then coated with Transbond XT light cure adhesive composition (3M), and adhered to a knurled steel bonding ring. The Transbond XT adhesive was then  
15 cured by exposing the Transbond XT adhesive to radiation emitted from an Ortholux XT Visible Light Curing Unit for 10 seconds.

The bonded cube was then tested according to the Bond Strength Test Method. The results are reported in Table II.

#### **20 Example 8**

The 0.231 cm x 0.330 cm surface of a 0.231 cm x 0.330 cm x 0.183 cm cube of Halar 500DA ethylene-chlorotrifluoroethylene copolymer (Ausimont) was primed and adhered to a grooved, knurled steel ring according to the method set forth in Example 6.

The bonded cube was then tested according to the Bond Strength Test  
25 Method. The results are reported in Table II.

### **Example 9**

The 0.231 cm x 0.330 cm surface of a 0.231 cm x 0.330 cm x 0.183 cm cube of Halar 500DA ethylene-chlorotrifluoroethylene copolymer (Ausimont) was primed and adhered to a grooved, knurled steel ring according to the method set forth in Example 7.

5        The bonded cube was then tested according to the Bond Strength Test Method. The results are reported in Table II.

### **Example 10**

10        A base surface of a test sample in a form depicted in Figs. 5 and 6 made from Teflon PFA340 perfluoroalkoxy fluorocarbon resin (DuPont) was primed and adhered to a grooved, knurled steel ring according to the method set forth in Example 6. The test sample was then tested according to the Bond Strength Test Method. The results are reported in Table II.

### **Example 11**

15        A base surface of a test sample in a form depicted in Figs. 5 and 6 made from Teflon PFA340 was primed and adhered to a grooved, knurled steel ring according to the method set forth in Example 7. The bonded bracket was then tested according to the Bond Strength Test Method. The results are reported in Table II.

20        For Examples 6-11, the bond strength ranged from 7 to 23 pounds ("lbs")/sample with an average of 16 lbs/sample. The failure mode was adhesive between the primer composition and the sample (i.e., the cube or the test sample).

**TABLE II**

Example	Bond Strength (lbs)	Standard Deviation
6	22	3.0
7	5	1.4
8	20	5.4
9	10	3.9
10	13	5.3
11	6	2.7

**5 Example 12**

A test sample formed from virgin Halar ethylene-chlorotrifluoroethylene copolymer (Ausimont), having a shape as depicted in FIGS. 5 and 6, was tested according to the Transmittance Test Procedure set forth above. Transmittance was measured through regions identified as 1, 2, 3, 4, 5 and 6 in FIG. 5. The results are  
10 shown in % transmittance versus wavelength (nm) in FIG. 7.

**Example 13**

A bracket made from Halar ethylene-chlorotrifluoroethylene copolymer (Ausimont), having a shape as depicted in FIGS. 3 and 4, was tested according to the  
15 Transmittance Test Procedure set forth above. Transmittance data was obtained at locations identified as A, B, C, D, 1, 2 and 3 on FIG. 3. The results are shown in % transmittance versus wavelength (nm) in FIG. 8.

**Example 14**

20 A bracket made from Teflon PFA tetrafluoroethylene-perfluorovinylether copolymer (DuPont), having a shape as depicted in FIGS. 3 and 4, was tested according to the Transmittance Test Procedure set forth above. Transmittance data was obtained at locations identified as A, B, C, D, 1, 2 and 3 in FIG. 3. The results are shown in % transmittance versus wavelength (nm) in FIG. 9.



### Example 15

A bracket made from Teflon PFA tetrafluoroethylene-perfluorovinylether copolymer (DuPont) having a shape similar to the shape depicted in FIGS. 3 and 4 but with an embedded metallic framework as depicted in FIG. 13, was tested according to the Transmittance Test Procedure set forth above. Transmittance data was obtained at locations identified as A, B, C, D, 1, 2 and 3 in FIG. 13. The results are shown in % transmittance versus wavelength (nm) in FIG. 10.

### Example 16

A bracket made from Tefzel 210 ethylene-tetrafluoroethylene copolymer (available from DuPont), having a shape as depicted in FIGS. 3 and 4, was tested according to the Transmittance Test Procedure set forth above. Transmittance data was obtained at locations identified as A, B, C, D, 1, 2 and 3 in FIG. 3. The results are shown in % transmittance versus wavelength (nm) in FIG. 11.

### Comparative Example 1

A test article made from Teflon® polytetrafluoroethylene (available from DuPont), having a shape as depicted in FIGS. 5 and 6, was tested according to the Transmittance Test Procedure set forth above. Transmittance data was obtained at locations identified as A, B, 1, 2, 3, 4, 5 and 6 in FIG. 5. The results are shown in % transmittance versus wavelength (nm) in FIG. 12.

Other embodiments are within the claims. For example, the article can be pretreated with a polymerization initiator including, e.g., the above-described organoborane amine complexes, and packaged in a suitable package, e.g., a kit. The articles that have been pretreated with a polymerization initiator can also be provided

with an adhesive precoat and packaged in a suitable package that optionally includes other components necessary to form an adhesive composition.

The article may include a metallic component, e.g., a framework. Orthodontic brackets 20 and 40 including a metal framework 22, 42 depicted by dotted lines are shown in FIGS. 13 and 14. One embodiment of a metallic framework 42 is shown in perspective view in FIG. 15. The metallic framework 22, 42 may be partially or wholly embedded in the body of the bracket 20, 40. The framework can be coated or otherwise colored, e.g., by ink, paint, or porcelain, to match the color of the tooth or the color of the fluoropolymeric material. Examples of a metallic framework are described in U.S. Patent 5,597,302 (Pospisil et al.), which is incorporated herein.

The article may also include a nonfluoropolymeric interior and a fluoropolymeric exterior layer. The fluoropolymeric exterior layer may extend over the entire surface of the nonfluoropolymeric interior or a portion thereof. Examples of suitable nonfluoropolymeric materials include glass, ceramic, plastic (e.g., polycarbonate and polyurethane), or a combination thereof. One example of such an article would include a polycarbonate bracket having an exterior fluoropolymeric layer, and, optionally, an exposed polycarbonate surface, which can be used for bonding the bracket to a tooth. Referring to FIG. 16, an orthodontic bracket 50 having a nonfluoropolymeric interior 52 and a fluoropolymeric layer 54 surrounding a portion of the nonfluoropolymeric interior 52 is shown. Surface 56 of nonfluoropolymeric interior 52 is exposed and is available for bonding to a tooth.

All of the patents, patent applications and test methods cited above are incorporated by reference into this document in total.

What is claimed is:

Sub  
a1

1. An orthodontic article comprising a fluoropolymer, said article exhibiting at least about 0.001 % transmittance at 546 nm when measured according to the Transmittance Test Procedure.

5 2. The article of claim 1, wherein said article exhibits a transmittance of at least about 0.001% over a wavelength range of from 400 nm to 800 nm when measured according to the Transmittance Test Procedure.

Bl

10 3. The article of claim 1, wherein said article exhibits a Delta E color shift of no greater than about 2 when tested according to the Hydrophilic Color Shift Test, and a Delta E color shift of no greater than about 5 when tested according to the Oleophilic Color Shift Test.

Sub  
a2

15 4. The article of claim 1, wherein said fluoropolymer is selected from the group consisting of perfluoroethylene-propylene copolymer, perfluoroalkoxyethylene, ethylene-tetrafluoroethylene copolymer, polyvinylidene fluoride, polyvinyl fluoride, polychlorotrifluoroethylene, ethylene-chlorotrifluoroethylene copolymer, or a combination thereof.

20 5. The article of claim 1, wherein said fluoropolymer comprises perfluoroethylene-propylene copolymer.

Bl

6. The article of claim 1, wherein said fluoropolymer comprises perfluoroalkoxyethylene.

25 Sub  
a3

7. The article of claim 1, wherein said fluoropolymer comprises ethylene-chlorotrifluoroethylene copolymer.

8. The article of claim 1 wherein said article comprises an orthodontic bracket.

5 9. The article of claim 1, further comprising a polymeric composition disposed on a surface of said article, said polymeric composition comprising an organoborane compound.

10 10. The article of claim 1, wherein said article exhibits at least about 0.01 % transmittance at 546 nm when measured according to the Transmittance Test Procedure.

15 11. The article of claim 1, further comprising an organoborane amine complex disposed on a surface of said article.

20 12. A method for using an orthodontic bracket, said method comprising: contacting a fluoropolymeric orthodontic bracket having an average transmittance of at least 0.001 % when measured according to the Transmittance Test Method with a composition comprising an organoborane compound; and adhering said bracket to a tooth.

25 13. The method of claim 12, wherein said fluoropolymeric orthodontic bracket exhibits a Delta E color shift of no greater than about 2 when tested according to the Hydrophilic Color Shift Test, and a Delta E color shift of no greater than about 5 when tested according to the Oleophilic Color Shift Test.

Sub  
at  
cont

B1

03 04 05 06 07 08 09 10 11 12 13 14 15 16 17 18 19 20 21 22 23 24 25 26 27 28 29 30 31 32 33 34 35 36 37 38 39 40 41 42 43 44 45 46 47 48 49 50 51 52 53 54 55 56 57 58 59 60 61 62 63 64 65 66 67 68 69 70 71 72 73 74 75 76 77 78 79 80 81 82 83 84 85 86 87 88 89 90 91 92 93 94 95 96 97 98 99 100 101 102 103 104 105 106 107 108 109 110 111 112 113 114 115 116 117 118 119 120 121 122 123 124 125 126 127 128 129 130 131 132 133 134 135 136 137 138 139 140 141 142 143 144 145 146 147 148 149 150 151 152 153 154 155 156 157 158 159 160 161 162 163 164 165 166 167 168 169 170 171 172 173 174 175 176 177 178 179 180 181 182 183 184 185 186 187 188 189 190 191 192 193 194 195 196 197 198 199 200 201 202 203 204 205 206 207 208 209 210 211 212 213 214 215 216 217 218 219 220 221 222 223 224 225 226 227 228 229 230 231 232 233 234 235 236 237 238 239 240 241 242 243 244 245 246 247 248 249 250 251 252 253 254 255 256 257 258 259 260 261 262 263 264 265 266 267 268 269 270 271 272 273 274 275 276 277 278 279 280 281 282 283 284 285 286 287 288 289 290 291 292 293 294 295 296 297 298 299 300 301 302 303 304 305 306 307 308 309 310 311 312 313 314 315 316 317 318 319 320 321 322 323 324 325 326 327 328 329 330 331 332 333 334 335 336 337 338 339 340 341 342 343 344 345 346 347 348 349 350 351 352 353 354 355 356 357 358 359 360 361 362 363 364 365 366 367 368 369 370 371 372 373 374 375 376 377 378 379 380 381 382 383 384 385 386 387 388 389 390 391 392 393 394 395 396 397 398 399 400 401 402 403 404 405 406 407 408 409 410 411 412 413 414 415 416 417 418 419 420 421 422 423 424 425 426 427 428 429 430 431 432 433 434 435 436 437 438 439 440 441 442 443 444 445 446 447 448 449 450 451 452 453 454 455 456 457 458 459 460 461 462 463 464 465 466 467 468 469 470 471 472 473 474 475 476 477 478 479 480 481 482 483 484 485 486 487 488 489 490 491 492 493 494 495 496 497 498 499 500 501 502 503 504 505 506 507 508 509 510 511 512 513 514 515 516 517 518 519 520 521 522 523 524 525 526 527 528 529 530 531 532 533 534 535 536 537 538 539 540 541 542 543 544 545 546 547 548 549 550 551 552 553 554 555 556 557 558 559 560 561 562 563 564 565 566 567 568 569 570 571 572 573 574 575 576 577 578 579 580 581 582 583 584 585 586 587 588 589 590 591 592 593 594 595 596 597 598 599 600 601 602 603 604 605 606 607 608 609 610 611 612 613 614 615 616 617 618 619 620 621 622 623 624 625 626 627 628 629 630 631 632 633 634 635 636 637 638 639 640 641 642 643 644 645 646 647 648 649 650 651 652 653 654 655 656 657 658 659 660 661 662 663 664 665 666 667 668 669 670 671 672 673 674 675 676 677 678 679 680 681 682 683 684 685 686 687 688 689 690 691 692 693 694 695 696 697 698 699 700 701 702 703 704 705 706 707 708 709 710 711 712 713 714 715 716 717 718 719 720 721 722 723 724 725 726 727 728 729 730 731 732 733 734 735 736 737 738 739 740 741 742 743 744 745 746 747 748 749 750 751 752 753 754 755 756 757 758 759 760 761 762 763 764 765 766 767 768 769 770 771 772 773 774 775 776 777 778 779 780 781 782 783 784 785 786 787 788 789 790 791 792 793 794 795 796 797 798 799 800 801 802 803 804 805 806 807 808 809 810 811 812 813 814 815 816 817 818 819 820 821 822 823 824 825 826 827 828 829 830 831 832 833 834 835 836 837 838 839 840 841 842 843 844 845 846 847 848 849 850 851 852 853 854 855 856 857 858 859 860 861 862 863 864 865 866 867 868 869 870 871 872 873 874 875 876 877 878 879 880 881 882 883 884 885 886 887 888 889 890 891 892 893 894 895 896 897 898 899 900 901 902 903 904 905 906 907 908 909 910 911 912 913 914 915 916 917 918 919 920 921 922 923 924 925 926 927 928 929 930 931 932 933 934 935 936 937 938 939 940 941 942 943 944 945 946 947 948 949 950 951 952 953 954 955 956 957 958 959 960 961 962 963 964 965 966 967 968 969 970 971 972 973 974 975 976 977 978 979 980 981 982 983 984 985 986 987 988 989 990 991 992 993 994 995 996 997 998 999 1000 1001 1002 1003 1004 1005 1006 1007 1008 1009 1010 1011 1012 1013 1014 1015 1016 1017 1018 1019 1020 1021 1022 1023 1024 1025 1026 1027 1028 1029 1030 1031 1032 1033 1034 1035 1036 1037 1038 1039 104

OK AS

bl

bl

20. The article of claim 17, wherein said article exhibits a Delta E color shift of no greater than about 2 when tested according to the Hydrophilic Color Shift Test, and a Delta E color shift of no greater than about 5 when tested according to the Oleophilic Color Shift Test.

21. The article of claim 17, wherein said article exhibits at least about 0.001 % transmittance at 546 nm when measured according to the Transmittance Test Procedure.

22. The article of claim 17, wherein said article exhibits at least about 0.01 % transmittance at 546 nm when measured according to the Transmittance Test Procedure.

23. The article of claim 17, wherein said article exhibits at least about 0.001% transmittance over a wavelength range of from 400 nm to 800 nm when measured according to the Transmittance Test Procedure.

24. The article of claim 17, further comprising an organoborane amine complex disposed on a surface of said article.

25. A kit for adhering an orthodontic article to a tooth, said kit comprising: an orthodontic article comprising a fluoropolymer having at least about 0.001% transmittance at 546 nm when measured according to the Transmittance Test Procedure; and

an adhesive system comprising

- a) a polymerizable component; and
- b) an organoborane amine complex.

26. The kit of claim 25, wherein said organoborane amine complex is disposed on a surface of said orthodontic article.

5

27. The kit of claim 25, further comprising a polyimide film.